



**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

BEST AVAILABLE COPY



PCT/EP200 4 / 0 0 7 8 0 5



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

REC'D 08 SEP 2004


WIPO PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Registration under the Companies Act does not constitute a new legal entity but merely affects the company to certain additional company law rules.



P. Mahoney

Signed

Dated 14 June 2004

Patents Form 1/77

Patents Act 1977
(Rule 16)The
Patent
Office

1/77

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference

MSP637

THE PATENT OFFICE

A

11 JUL 2003

NEWPORT

11 JUL 2003

2. Patent application number

(The Patent Office will fill in this part)

0316268.2

11JUL03 E821959-1 002914
P01/7700 0.00-0316268.23. Full name, address and postcode of the or of each applicant (*underline all surnames*)DOW CORNING CORPORATION
Midland
Michigan 48611
USAPatents ADP number (*if you know it*)

8506040002

If the applicant is a corporate body, give the country/state of its incorporation

USA/Michigan

4. Title of the invention

PROCESS FOR PREPARING CYCLIC ORGANOHYDROGENSILOXANES

5. Name of your agent (*if you have one*)

P V Davies

"Address for service" in the United Kingdom to which all correspondence should be sent (*including the postcode*)DOW CORNING LIMITED
Intellectual Property Department
Cardiff Road
Barry
CF63 2YLPatents ADP number (*if you know it*)

7804594001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (*if you know it*) the or each application number

Country

Priority application number
(*if you know it*)Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (*Answer 'Yes' if:*

Yes

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form.
Do not count copies of the same document

Continuation sheets of this form

Description	7	cf
Claim(s)	1	
Abstract		
Drawing(s)	1 + 1	

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77) 1

Request for substantive examination (Patents Form 10/77)

Any other documents 1 fee sheet
(please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature
P V Davies

Date
10/07/03

12. Name and daytime telephone number of person to contact in the United Kingdom P V Davies 01446 723505

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

PROCESS FOR PREPARING CYCLIC ORGANOHYDROGENSILOXANES

BACKGROUND OF INVENTION

5 [0001] The present invention is a process for preparing cyclic organohydrogensiloxanes.

[0002] Cyclic organohydrogensiloxanes such as cyclic methylhydrogensiloxane are useful as crosslinkers in silicone coatings and encapsulating materials used in the electronic industry and in release paper coatings and can be used as intermediates to form SiH functional siloxanes. In typical processes for preparing organohydrogensiloxanes a first step involves the hydrolysis of an organohydrogendichlorosilane to form an equilibrium mixture containing cyclic organohydrogensiloxanes and short-chain linear organohydrogensiloxanes. Generally, the weight percent of cyclic organohydrogensiloxanes in the equilibrium mixture is small in relation to the weight percent of linear organohydrogensiloxanes present. Consequently when demand for cyclic organohydrogensiloxanes is high, an excess of linear organohydrogensiloxanes may be produced.

[0003] US-A-5395956 describes a process comprising contacting an organohydrogendichlorosilane with about a stoichiometric equivalent of water to form a hydrolyzate, diluting the hydrolyzate in an inert solvent and contacting it with an acidic rearrangement catalyst to effect formation of cyclic organohydrogensiloxanes. The catalyst is generally a heterogeneous catalyst used as a fixed-bed or stirred-bed. US-A-5395956 says that the acidic rearrangement catalyst can be a homogeneous catalyst such as hydrogen chloride, sulfuric acid, or chlorosulfonic acid, but that such homogeneous acids are generally not preferred since they must subsequently be neutralized.

SUMMARY OF INVENTION

30 [0004] A process according to the present invention for preparing cyclic organohydrogensiloxanes comprises (A) contacting a silane of the formula $RHSiCl_2$, where R is selected from alkyl radicals having 1 to 12 carbon atoms and aryl radicals, with water to

form a hydrolyzate comprising cyclic organohydrogensiloxanes and linear organohydrogensiloxanes, and (B) contacting the hydrolyzate with an acidic rearrangement catalyst in the presence of an inert liquid diluent to increase the ratio of the cyclic organohydrogensiloxanes to linear organohydrogensiloxanes in the hydrolyzate, characterised in that the acidic rearrangement catalyst is an organic compound containing a strong acid group which is dissolved in the inert liquid diluent present.

[0005] The process of the invention is preferably carried out as a continuous process including the steps of (C) recovering the cyclic methylhydrogensiloxanes by separation from the linear methylhydrogensiloxanes and diluent, and (D) recycling the linear methylhydrogensiloxanes and diluent containing dissolved acidic rearrangement catalyst from Step (C) to Step (B). The organic acidic rearrangement catalyst is thus continuously recycled through the rearrangement (B) and separation (C) steps with the inert diluent.

[0006] We have found that when the process of US-A-5395956 is operated using a fixed bed solid catalyst as described therein, equilibration to increase the ratio of the cyclic organohydrogensiloxanes to linear organohydrogensiloxanes in the hydrolyzate takes place initially, but the activity of the catalyst for this rearrangement fairly rapidly decreases over time. In the process of the present invention, the organic acid catalyst which is dissolved in the inert diluent retains its catalytic activity for increasing the ratio of the cyclic organohydrogensiloxanes to linear organohydrogensiloxanes in the hydrolyzate for a much longer time than the fixed bed solid catalyst.

DETAILED DESCRIPTION OF INVENTION

[0007] Silanes which can be hydrolyzed in the present process are described by formula (1). The silane may be a single species of silane as described by formula (1) or may be a mixture of such silanes. The silane contains substituent R, where R is selected from a group consisting of saturated monovalent hydrocarbon radicals comprising one to 12 carbon atoms and aryl radicals. R can be, for example, methyl, ethyl, propyl, isopropyl, butyl, tertiary butyl, sec-butyl, hexyl, cyclohexyl, dodecyl, phenyl, tolyl, and naphthyl. Preferred is

when R is selected from a group consisting of methyl and phenyl. Most preferred is when R is methyl, i.e. methyldichlorosilane.

[0008] The silane is contacted with about a stoichiometric equivalent of water, where a stoichiometric equivalent of water is defined as 0.5 mole of water per mole of chlorine provided to the process by the silane. By use of the term "about" it is meant that the mole ratio of water to silane is within a range of plus or minus 20 percent of stoichiometric equivalence. Preferred is when the mole ratio of water to silane is within a range of -5% to +15%, more preferably from stoichiometric equivalence to an excess of 5 or 10% water.

[0009] Contact of the silane with water in step (A) can be conducted in standard reactors for hydrolyzing chlorosilanes. Although the pressure at which the process is conducted is not critical, it is preferred that the process be conducted at a pressure at which the silane is present as a liquid phase. Such pressure will be dependent upon the particular chlorosilane and the temperature at which the process is conducted. The hydrolysis process is preferably conducted at a temperature within a range from -15°C to 120°C, more preferably 0°C to 50°C, most preferably 20°C to 40°C.

[0010] The hydrolyzate formed in the hydrolysis process is diluted in an inert liquid diluent, which may or may not be miscible with the hydrolyzate. By the term "inert" it is meant a diluent which does not otherwise have significant reaction in the process. Preferred liquid diluents are alkanes, including mixtures of alkanes. The alkanes can be linear or branched alkanes or a mixture thereof. The liquid diluent preferably has a boiling point above that of the cyclic hexamer of the organohydrogensiloxane. For example when the cyclic hexamer is methylhydrogensiloxane, suitable diluents are those alkanes having greater than about nine carbon atoms. One preferred diluent is the paraffin mixture of boiling point range 243°C to 285°C sold under the Trade Mark 'Isopar P'. Inert liquid diluents having a boiling point below that of the cyclic hexamer of the organohydrogensiloxane can also be used, but may make separation of the diluent from the cyclic organohydrogensiloxane more difficult.

[0011] The optimal weight ratio of hydrolyzate to diluent will depend upon such factors as the organic substituent substituted on the silicon atoms and the desired ratio of

cyclic organohydrogensiloxane to linear organohydrogensiloxane in the rearranged hydrolyzate at equilibrium. Up to a certain maximum, the greater the dilution of the hydrolyzate the greater the ratio of the cyclic organohydrogensiloxanes to linear organohydrogensiloxanes in the rearranged hydrolyzate. The diluent preferably forms about 50 to 95% by weight of the liquid mixture of hydrolyzate and diluent, more preferably 60 to 90%, most preferably 70 to 85%.

[0012] The diluted hydrolyzate is contacted with the organic acid rearrangement catalyst. It is generally preferred that the hydrolyzate is not contacted with the acidic rearrangement catalyst before being diluted. When the process of the invention is carried out as a continuous process including recycling of the linear methylhydrogensiloxanes and diluent containing dissolved acidic rearrangement catalyst, the diluent which contacts the hydrolyzate will contain the catalyst.

[0013] The acidic rearrangement catalyst is an organic compound containing a strong acid group which is dissolved in the inert liquid diluent present. By a strong acid group we mean that the organic acid has a pK of less than 3 and preferably less than 1.5. The acid is preferably a sulphonic acid but could alternatively be a phosphonic acid or an acid sulphate ester. Preferred sulphonic acids are aryl sulphonic acids, particularly alkylaryl sulphonic acids of the formula $R'-Ar-SO_3H$, where Ar is an aromatic nucleus such as a benzene or naphthalene nucleus and R' is an alkyl group which may have 1 to 30 carbon atoms but preferably has 8 to 20 carbon atoms, for example dodecylbenzenesulphonic acid. Alternative sulphonic acids which are suitable include alkyl sulphonic acids and halogenated aryl or alkyl sulphonic acids, for example trifluoromethane sulphonic acid.

[0014] The concentration of acidic rearrangement catalyst in the inert liquid diluent is preferably in the range 0.05 to 5% by weight, more preferably 0.07 to 0.2% by weight. In a continuous process, the concentration can be monitored as the linear methylhydrogensiloxanes and diluent containing dissolved acidic rearrangement catalyst is recycled from the separation step (C) to the rearrangement step (B), and can be adjusted by adding more catalyst or more diluent as required.

[0015] The temperature at which the rearrangement reaction is carried out is not critical and can generally be within a range of greater than about the freezing point of the inert diluent to about 150°C. Preferred is a temperature within a range of about 0°C to 40°C, for example ambient temperature. The pressure at which the arrangement process is run is not critical and can be ambient pressure.

[0016] The vessel in which the rearrangement reaction is carried out can be any type of tank or reactor, for example a simple tank which optionally is stirred or a tube reactor. The reaction time can be from 1 minute to 24 hours or more; the rearrangement reaction is an equilibration reaction and equilibration is generally going on wherever the catalyst exists in contact with the siloxane and the solvent. Typical residence times of the catalyst, siloxane and solvent in a continuous process in which the catalyst is continuously recycled through the rearrangement and separation steps with the inert diluent are between 0.5 and 10 hours, particularly 1 to 5 hours. Since the rearrangement reaction is an equilibration reaction prolonged contact times are not harmful.

[0017] The cyclic organohydrogensiloxanes which can be recovered by the present process are described by formula $(RHSiO)_n$, where R is as previously described and n is an integer from three to about 12. The preferred organohydrogensiloxanes recovered from the present process are those where R is methyl and n is four, five, or six. The method for recovering the cyclic organohydrogensiloxanes from the present process is not critical and can be standard methods known in the art for separating cyclic siloxanes from mixtures. For example, the rearranged hydrolyzate can be flash distilled to separate the cyclic organohydrogensiloxanes from higher-boiling linear organohydrogensiloxanes and the bulk of the inert liquid diluent. The recovered higher-boiling linear organohydrogensiloxanes and diluent, and the catalyst dissolved therein, can be recycled to the rearrangement reactor. The recovered lower-boiling fraction containing the cyclic organohydrogensiloxanes can if desired be treated with additional water to effect polymerization of low-boiling linear species to higher boiling linear species and facilitate their separation from the cyclic organohydrogensiloxanes. The resulting water phase can be removed by standard methods such as gravimetric or membrane separation. The cyclic organohydrogensiloxane-containing fraction can then be distilled to separate the cyclic organohydrogensiloxanes from higher-

boiling linear species. The higher-boiling linear species can then be recycled to the rearrangement reactor for further processing.

[0018] The following Example, in which percentages are by weight, is provided to illustrate the present invention. The Example includes the single Figure of the accompanying drawings, which is a graph showing concentration of cyclic organohydrogensiloxanes in the mixture exiting the rearrangement reactor of Example 1 against time and also the yield of cyclic organohydrogensiloxanes in Example 1 against time expressed as % of the theoretical yield based on chlorosilane feed.

Example 1

[0019] Methylchlorosilane CH_3SiCl_2 was mixed with a stoichiometric equivalent of water, i.e. 0.5 mole of water per mole of silicon bonded chlorine, in a steam heated continuous hydrolysis reactor. The hydrolysis reactor was maintained at 60 psig and the temperature of the reactor was controlled such that the hydrolyzate exiting the reactor was at a temperature of about 33°C . The hydrolyzate exiting the reactor was analyzed by gas chromatography (GC) using a flame ionization detector (FID) and found to comprise about 95 weight percent linear chlorine end-terminated methylhydrogensiloxane species and about five weight percent cyclic methylhydrogensiloxanes species. The hydrolyzate was diluted to about 20% in 'Isopar P' hydrocarbon solvent containing 0.1% dodecylbenzenesulphonic acid catalyst. Excess HCl gas from the hydrolysis reaction was collected for re-use.

[0020] The diluted hydrolyzate containing catalyst was fed through a simple rearrangement reactor tank at ambient temperature and pressure. Residence time of the diluted hydrolyzate in the reactor was about 3 hours. GC-FID analysis of the product exiting the rearrangement reactor showed the siloxane component to consist of about 70 weight percent linear chlorine end-terminated methylhydrogensiloxane species and about 30 weight percent cyclic methylhydrogensiloxane species.

[0021] The product from the rearrangement reactor was heated to drive off aqueous HCl , stripped in flash drums under vacuum and then vacuum distilled and the cyclic species

and low-boiling linear species taken overhead. The bottom fraction was cooled and recycled to the rearrangement reactor.

5 [0022] Residual chlorine in the overhead fraction from the flash distillation (the crude product) was removed by contact with a calcium carbonate calcium chloride water system. The product was finally dried in a magnesium oxide bed. The recovered cyclic methylhydrogensiloxane fraction was analyzed by GC-FID and found to comprise 99.7 weight percent cyclic methylhydrogensiloxanes of the tetramer, pentamer, and hexamer species. The process was run continuously for about 20 days.

10 [0023] The results are shown in Figure 1. The % cyclics in the mixture exiting the rearrangement reactor was consistently above 4% and on average above 5%. The yield of cyclic methylhydrogensiloxanes was consistently above 80% of the theoretical yield based on chlorosilane feed, and on average about 100% of the theoretical yield. The % of theoretical
15 equilibrium data is a comparison with an empirical relationship between siloxane and cyclics equilibrium concentration from lab. experiments using a "standard" solid catalyst, Amberlyst(Trade Mark) sulphonated divinylbenzene styrene copolymer.

20 [0024] When the process of Example 1 was carried out using a fixed bed of solid catalyst in the rearrangement reactor, as described in US-A-5395956, instead of adding dodecylbenzenesulphonic acid catalyst to the solvent, the % cyclics in the mixture exiting the rearrangement reactor was variable but usually in the range 1% to 3%.

CLAIMS:

1. A process for preparing cyclic organohydrogensiloxanes comprising:
(A) contacting a silane of the formula RHSiCl_2 , where R is selected from alkyl radicals having 1 to 12 carbon atoms and aryl radicals, with water to form a hydrolyzate comprising cyclic organohydrogensiloxanes and linear organohydrogensiloxanes, and (B) contacting the hydrolyzate with an acidic rearrangement catalyst in the presence of an inert liquid diluent to increase the ratio of the cyclic organohydrogensiloxanes to linear organohydrogensiloxanes in the hydrolyzate, characterised in that the acidic rearrangement catalyst is an organic compound containing a strong acid group which is dissolved in the inert diluent present.
2. A process according to Claim 1, characterised in that the acidic rearrangement catalyst is a sulphonic acid.
3. A process according to Claim 2, characterised in that the sulphonic acid is an alkylaryl sulphonic acid.
4. A process according to Claim 3, characterised in that the sulphonic acid is dodecylbenzenesulphonic acid.
5. A process according to any of Claims 1 to 4, characterised in that the process is a continuous process including the steps of (C) recovering the cyclic methylhydrogensiloxanes by separation from the linear methylhydrogensiloxanes and diluent, and (D) recycling the linear methylhydrogensiloxanes and diluent containing dissolved acidic rearrangement catalyst from Step (C) to Step (B).
6. A process according to any of Claims 1 to 5, characterised in that the concentration of acidic rearrangement catalyst in the diluent is in the range 0.05 to 5% by weight.

